

### Technical Standard of Annealing of Tungsten and Its Alloys

Mark	Annealing Electricity of Vertical Sintering Furnace/A		Annealing Temperature of Welding Furnace
	$\phi 10.0$ mm	$\phi 9.4$ mm	$\phi 8.8$ mm
W, WAI	2300 ~ 2500	2100 ~ 2300	1750 $\pm$ 50
WCe	2600 ~ 2800	2400 ~ 2600	-
WRe	-	1500 ~ 1700	-
Soaking Time/min	4 ~ 5	4 ~ 5	90 ~ 120